

FILE

Formulations of patches

Project No. _____

Book No. 24

143

om Page No. _____

with Nategiline free base

with and without 1.2 Propanediol

#1) 1430 / 26 ³⁵ 1.2 PD / 15 Sel		without 1.2 PD		
		solids	liq	1/3 liq
GMS 1430 (41% sol)		85.0	207.3	69.1
1.2 PD	26.0	0.0	0.0	0.0
Sel free base	11.3	15.0	15.0	5.0
Et OH	30.0	30.0	30.0	10.0

#2) 1430 / 35 1.2 PD / 15 Sel		with 1.2 PD		
		solids	liq	1/3 liq
GMS 1430 (41%)		50.0	121.95	40.7
1.2 PD		35.0	35.0	11.7
Sel (free base)		15.0	15.0	5.0
Et OH		20.0	20.0	7.0

To Page No. _____

Witnessed & Understood by me,

Date

Invented by

Date

Recorded by

Libertine

44

Project No. _____

Book No. 24

TITLE

Formulation (cont)

TITLE

Pec

From Page No. _____

#3

1753 / 1.2 PD / 15 Selwithout 1.2 PD

	<u>solids</u>	<u>liq.</u>	<u>1/3 liq.</u>
<u>Gelva 1753 (28.3%)</u>	<u>85.0</u>	<u>303.6</u>	<u>101.2</u>
<u>1.2 PD</u>	<u>0.0</u>	<u>0.0</u>	<u>0.0</u>
<u>Del (free base)</u>	<u>15.0</u>	<u>15.0</u>	<u>5.0</u>
<u>EtOH</u>	<u>30.0</u>	<u>30.0</u>	<u>10.0</u>

Del was mixed with EtOH and added to 1753
while mixing.

#4

1753 / 35 1.2 PD / 15 Sel

	<u>solids</u>	<u>liq.</u>	<u>1/3 liq.</u>
<u>Gelva 1753 / 35 1.2 PD / 15 Sel</u>			
<u>Gelva 1753</u>	<u>50.0</u>	<u>176.7</u>	<u>58.9</u>
<u>1.2 PD</u>	<u>35.0</u>	<u>35.0</u>	<u>11.7</u>
<u>Del (free base)</u>	<u>15.0</u>	<u>15.0</u>	<u>5.0</u>
<u>EtOH</u>	<u>20.0</u>	<u>20.0</u>	<u>7.0</u>

EtOH was added to 1753

Del was mixed with 1.2 PD and added to
1753 while mixing

To Page No. _____

Witnessed & Understood by me,

Date

Invented by

Date

Recorded by

Witnessed & I

Liz Coe